

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 08-283343

(43)Date of publication of application : 29.10.1996

(51)Int.Cl.

C08F210/06

C08F 4/642

C08F210/08

(21)Application number : 07-087248

(71)Applicant : MITSUI PETROCHEM IND LTD

(22)Date of filing : 12.04.1995

(72)Inventor : IMUDA JUNICHI
HASHIMOTO MIKIO

(54) PROPYLENE ELASTOMER

(57)Abstract:

PURPOSE: To obtain a propylene elastomer excellent in rigidity, heat resistance, scratch resistance, transparency, etc., by selecting an elastomer comprising a specified amount of propylene units and a specified amount of 1-butene units and having specified properties.

CONSTITUTION: An elastomer comprising 50-95mol% propylene units (A) and 5-50mol% 1-butene units (B) and having such properties that, when the ^{13}C -NMR spectrum of the side chain CH_3 groups of the second unit A of a chain composed of three head-to-tail-bonded As or of a propylene/butene chain composed of three head-to-tail-bonded As and Bs and containing A as the second unit is measured and the total area of the peaks appearing in the range of 19.5-21.9ppm is taken as 100%, the area of the peak appearing in the range of 21.0-21.9ppm is 90% or above, that the intrinsic viscosity is 0.1-12dl/g as measured in decalin at 135° , that the molecular weight distribution (M_w/M_n) as determined by GPC is 3 or below, and that the parameter B value representing the randomness of the comonomer chain distribution is 1.0-1.5.

LEGAL STATUS

[Date of request for examination] 12.03.2002

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number] 3570772

[Date of registration] 02.07.2004

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office